

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Awning - Outswing	NCW-K-4-00108-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.27	19	0.34	0.49	55
Awning - Outswing	NCW-K-4-00108-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.29	1.65	0.25	18	0.34	0.44	55
Awning - Outswing	NCW-K-4-00108-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.29	1.65	0.23	17	0.34	0.40	55
Awning - Outswing	NCW-K-4-00130-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.27	19	0.34	0.49	55
Awning - Outswing	NCW-K-4-00131-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.23	12	0.34	0.40	55
Awning - Outswing	NCW-K-4-00132-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.25	14	0.34	0.44	55
Awning - Outswing	NCW-K-4-00112-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.27	23	0.34	0.47	47
Awning - Outswing	NCW-K-4-00112-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.24	21	0.34	0.43	47
Awning - Outswing	NCW-K-4-00112-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.26	1.48	0.22	20	0.34	0.39	47
Awning - Outswing	NCW-K-4-00109-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.27	19	0.34	0.48	57
Awning - Outswing	NCW-K-4-00111-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.25	16	0.34	0.44	57
Awning - Outswing	NCW-K-4-00110-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.23	15	0.34	0.40	57
Awning - Outswing	NCW-K-4-00133-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.27	18	0.34	0.48	54
Awning - Outswing	NCW-K-4-00134-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.23	12	0.34	0.40	54
Awning - Outswing	NCW-K-4-00135-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.25	14	0.34	0.44	54
Awning - Outswing	NCW-K-4-00113-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.26	22	0.34	0.47	46
Awning - Outswing	NCW-K-4-00115-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.24	21	0.34	0.43	46
Awning - Outswing	NCW-K-4-00114-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.27	1.53	0.22	18	0.34	0.38	46
Awning - Outswing	NCW-K-4-00136-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.27	1.53	0.27	21	0.34	0.47	44
Awning - Outswing	NCW-K-4-00137-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.22	16	0.34	0.39	44
Awning - Outswing	NCW-K-4-00138-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.28	1.59	0.24	18	0.34	0.43	44
Awning - Outswing	NCW-K-4-00139-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.27	1.53	0.27	21	0.34	0.47	44
Awning - Outswing	NCW-K-4-00140-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.22	16	0.34	0.38	43
Awning - Outswing	NCW-K-4-00141-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.22	16	0.34	0.38	43
Awning - Outswing	NCW-K-4-00154-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.50	31	0.34	0.47	57

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Awning - Outswing	NCW-K-4-00154-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.46	29	0.34	0.47	57
Awning - Outswing	NCW-K-4-00154-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.41	26	0.34	0.47	57
Awning - Outswing	NCW-K-4-00155-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.49	30	0.34	0.47	56
Awning - Outswing	NCW-K-4-00156-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.41	24	0.34	0.47	56
Awning - Outswing	NCW-K-4-00157-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.45	27	0.34	0.47	56
Awning - Outswing	NCW-K-4-00158-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.50	30	0.34	0.47	55
Awning - Outswing	NCW-K-4-00159-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.41	21	0.34	0.47	54
Awning - Outswing	NCW-K-4-00160-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.46	25	0.34	0.47	54
Awning - Outswing	NCW-K-4-00161-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.49	29	0.34	0.47	54
Awning - Outswing	NCW-K-4-00162-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.41	21	0.34	0.47	54
Awning - Outswing	NCW-K-4-00163-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.45	24	0.34	0.47	54
Awning - Outswing	NCW-K-4-00164-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.24	21	0.34	0.46	45
Awning - Outswing	NCW-K-4-00165-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.27	1.53	0.20	17	0.34	0.37	45
Awning - Outswing	NCW-K-4-00166-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.22	20	0.34	0.41	45
Casement - French - Outswing	NCW-K-18-00061-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.25	17	0.08	0.44	58
Casement - French - Outswing	NCW-K-18-00063-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.30	1.70	0.23	16	0.08	0.39	58
Casement - French - Outswing	NCW-K-18-00062-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.21	10	0.08	0.35	58
Casement - French - Outswing	NCW-K-18-00067-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.24	19	0.08	0.42	47
Casement - French - Outswing	NCW-K-18-00068-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.30	1.70	0.20	14	0.08	0.34	44
Casement - French - Outswing	NCW-K-18-00069-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.22	16	0.08	0.38	47
Casement - French - Outswing	NCW-K-18-00070-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.24	19	0.08	0.42	46
Casement - French - Outswing	NCW-K-18-00071-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.30	1.70	0.20	14	0.08	0.34	45
Casement - French - Outswing	NCW-K-18-00072-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.22	16	0.08	0.38	46
Casement - French - Outswing	NCW-K-18-00065-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.21	10	0.08	0.35	57
Casement - French - Outswing	NCW-K-18-00066-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.23	12	0.08	0.39	57

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Casement - French - Outswing	NCW-K-18-00064-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.25	17	0.08	0.43	57
Casement - French - Outswing	NCW-K-18-00085-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.45	26	0.08	0.50	57
Casement - French - Outswing	NCW-K-18-00086-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.35	1.99	0.37	18	0.08	0.40	57
Casement - French - Outswing	NCW-K-18-00087-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.34	1.93	0.41	21	0.08	0.45	57
Casement - French - Outswing	NCW-K-18-00088-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.44	25	0.08	0.50	57
Casement - French - Outswing	NCW-K-18-00089-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.35	1.99	0.36	17	0.08	0.40	57
Casement - French - Outswing	NCW-K-18-00090-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.34	1.93	0.40	21	0.08	0.45	57
Casement - French - Outswing	NCW-K-18-00091-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.27	1.53	0.22	19	0.08	0.41	45
Casement - French - Outswing	NCW-K-18-00092-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.18	14	0.08	0.33	45
Casement - French - Outswing	NCW-K-18-00093-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.20	15	0.08	0.37	45
Casement - Outswing	NCW-K-3-00305-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.28	20	0.20	0.50	59
Casement - Outswing	NCW-K-3-00305-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.29	1.65	0.26	19	0.20	0.45	59
Casement - Outswing	NCW-K-3-00305-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.29	1.65	0.23	17	0.20	0.41	59
Casement - Outswing	NCW-K-3-00327-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.28	20	0.20	0.50	57
Casement - Outswing	NCW-K-3-00328-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.24	12	0.20	0.41	57
Casement - Outswing	NCW-K-3-00329-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.26	15	0.20	0.45	57
Casement - Outswing	NCW-K-3-00309-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.25	1.42	0.27	24	0.20	0.49	48
Casement - Outswing	NCW-K-3-00309-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.25	1.42	0.25	23	0.20	0.44	48
Casement - Outswing	NCW-K-3-00309-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.25	1.42	0.23	22	0.20	0.40	48
Casement - Outswing	NCW-K-3-00306-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.28	20	0.20	0.50	58
Casement - Outswing	NCW-K-3-00308-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.30	1.70	0.26	17	0.20	0.45	58
Casement - Outswing	NCW-K-3-00307-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.23	16	0.20	0.41	58
Casement - Outswing	NCW-K-3-00330-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.28	20	0.20	0.50	56
Casement - Outswing	NCW-K-3-00331-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.23	12	0.20	0.41	56

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Casement - Outswing	NCW-K-3-00332-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.26	15	0.20	0.45	56
Casement - Outswing	NCW-K-3-00310-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.25	1.42	0.27	24	0.20	0.48	47
Casement - Outswing	NCW-K-3-00312-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.26	1.48	0.25	22	0.20	0.44	47
Casement - Outswing	NCW-K-3-00311-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.26	1.48	0.23	21	0.20	0.39	47
Casement - Outswing	NCW-K-3-00333-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.27	23	0.20	0.49	46
Casement - Outswing	NCW-K-3-00334-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.23	17	0.20	0.40	45
Casement - Outswing	NCW-K-3-00335-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.28	1.59	0.25	19	0.20	0.44	46
Casement - Outswing	NCW-K-3-00336-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.27	23	0.20	0.48	45
Casement - Outswing	NCW-K-3-00337-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.23	17	0.20	0.39	45
Casement - Outswing	NCW-K-3-00338-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.28	1.59	0.25	19	0.20	0.44	45
Casement - Outswing	NCW-K-3-00351-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.51	32	0.20	0.57	58
Casement - Outswing	NCW-K-3-00351-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.47	29	0.20	0.52	58
Casement - Outswing	NCW-K-3-00351-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.43	27	0.20	0.47	58
Casement - Outswing	NCW-K-3-00352-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.51	32	0.20	0.57	57
Casement - Outswing	NCW-K-3-00353-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.42	25	0.20	0.46	57
Casement - Outswing	NCW-K-3-00354-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.46	28	0.20	0.52	57
Casement - Outswing	NCW-K-3-00355-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.51	31	0.20	0.57	56
Casement - Outswing	NCW-K-3-00356-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.42	22	0.20	0.47	56
Casement - Outswing	NCW-K-3-00357-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.47	26	0.20	0.52	56
Casement - Outswing	NCW-K-3-00358-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.50	30	0.20	0.57	55
Casement - Outswing	NCW-K-3-00359-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.42	22	0.20	0.46	55
Casement - Outswing	NCW-K-3-00360-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.46	25	0.20	0.52	55
Casement - Outswing	NCW-K-3-00361-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.25	1.42	0.25	23	0.20	0.47	46
Casement - Outswing	NCW-K-3-00362-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.27	1.53	0.21	18	0.20	0.38	46
Casement - Outswing	NCW-K-3-00363-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.23	21	0.20	0.43	46

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Casement - Outswing	NCW-K-3-00364-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.25	18	0.20	0.47	41
Casement - Outswing - Roll Down Screen	NCW-K-23-00091-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.25	18	0.20	0.44	59
Casement - Outswing - Roll Down Screen	NCW-K-23-00091-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.29	1.65	0.23	17	0.20	0.40	59
Casement - Outswing - Roll Down Screen	NCW-K-23-00091-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL ≥1"	0.29	1.65	0.21	16	0.20	0.36	59
Casement - Outswing - Roll Down Screen	NCW-K-23-00113-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.25	18	0.20	0.44	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00114-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL ≥1"	0.32	1.82	0.21	12	0.20	0.36	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00115-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.31	1.76	0.23	14	0.20	0.40	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00095-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.24	21	0.20	0.43	48
Casement - Outswing - Roll Down Screen	NCW-K-23-00095-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.26	1.48	0.22	20	0.20	0.39	48
Casement - Outswing - Roll Down Screen	NCW-K-23-00095-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL ≥1"	0.26	1.48	0.20	19	0.20	0.35	48
Casement - Outswing - Roll Down Screen	NCW-K-23-00092-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.25	18	0.20	0.44	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00094-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.30	1.70	0.23	16	0.20	0.40	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00093-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL ≥1"	0.30	1.70	0.21	14	0.20	0.35	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00116-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.25	18	0.20	0.44	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00117-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL ≥1"	0.32	1.82	0.21	12	0.20	0.35	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00118-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.31	1.76	0.23	14	0.20	0.40	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00096-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.24	21	0.20	0.43	47
Casement - Outswing - Roll Down Screen	NCW-K-23-00098-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.26	1.48	0.22	20	0.20	0.38	47
Casement - Outswing - Roll Down Screen	NCW-K-23-00097-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL ≥1"	0.27	1.53	0.20	18	0.20	0.34	47
Casement - Outswing - Roll Down Screen	NCW-K-23-00119-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.24	21	0.20	0.43	46
Casement - Outswing - Roll Down Screen	NCW-K-23-00120-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL ≥1"	0.29	1.65	0.20	15	0.20	0.35	44
Casement - Outswing - Roll Down Screen	NCW-K-23-00121-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.28	1.59	0.22	17	0.20	0.39	46
Casement - Outswing - Roll Down Screen	NCW-K-23-00122-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.24	21	0.20	0.43	45
Casement - Outswing - Roll Down Screen	NCW-K-23-00123-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL ≥1"	0.29	1.65	0.20	15	0.20	0.34	45
Casement - Outswing - Roll Down Screen	NCW-K-23-00124-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.28	1.59	0.22	17	0.20	0.38	45

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Casement - Outswing - Roll Down Screen	NCW-K-23-00137-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.46	29	0.20	0.51	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00137-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.41	26	0.20	0.46	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00137-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.37	24	0.20	0.41	58
Casement - Outswing - Roll Down Screen	NCW-K-23-00138-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.45	28	0.20	0.50	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00139-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.37	22	0.20	0.40	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00140-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.41	26	0.20	0.45	57
Casement - Outswing - Roll Down Screen	NCW-K-23-00141-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.45	28	0.20	0.51	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00142-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.37	20	0.20	0.41	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00143-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.41	23	0.20	0.46	56
Casement - Outswing - Roll Down Screen	NCW-K-23-00144-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.45	28	0.20	0.50	55
Casement - Outswing - Roll Down Screen	NCW-K-23-00145-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.37	20	0.20	0.40	55
Casement - Outswing - Roll Down Screen	NCW-K-23-00146-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.41	23	0.20	0.45	55
Double Hung	NCW-K-1-00200-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.50	30	0.21	0.56	53
Double Hung	NCW-K-1-00200-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.45	27	0.21	0.50	53
Double Hung - Roll Up Screen	NCW-K-1-00200-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.50	30	0.21	0.56	53
Double Hung - Roll Up Screen	NCW-K-1-00200-00004	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.45	27	0.21	0.50	53
Double Hung	NCW-K-1-00201-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.32	1.82	0.45	26	0.21	0.50	53
Double Hung - Roll Up Screen	NCW-K-1-00201-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.32	1.82	0.45	26	0.21	0.50	53
Double Hung	NCW-K-1-00202-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.34	1.93	0.40	20	0.21	0.44	53
Double Hung - Roll Up Screen	NCW-K-1-00202-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.34	1.93	0.40	20	0.21	0.44	53
Double Hung	NCW-K-1-00203-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL <1"	0.33	1.87	0.45	25	0.21	0.50	53
Double Hung - Roll Up Screen	NCW-K-1-00203-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL <1"	0.33	1.87	0.45	25	0.21	0.55	53
Double Hung	NCW-K-1-00204-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.27	18	0.21	0.49	54
Double Hung	NCW-K-1-00204-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.30	1.70	0.25	17	0.21	0.44	54
Double Hung - Roll Up Screen	NCW-K-1-00204-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.27	18	0.21	0.49	54

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Double Hung - Roll Up Screen	NCW-K-1-00204-00004	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.30	1.70	0.25	17	0.21	0.44	54
Double Hung	NCW-K-1-00205-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.31	1.76	0.25	15	0.21	0.44	54
Double Hung - Roll Up Screen	NCW-K-1-00205-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.31	1.76	0.25	15	0.21	0.44	54
Double Hung	NCW-K-1-00206-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.33	1.87	0.22	11	0.21	0.38	54
Double Hung - Roll Up Screen	NCW-K-1-00206-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.33	1.87	0.22	11	0.21	0.38	54
Double Hung	NCW-K-1-00207-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.32	1.82	0.25	14	0.21	0.44	54
Double Hung - Roll Up Screen	NCW-K-1-00207-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.32	1.82	0.22	13	0.21	0.44	54
Double Hung	NCW-K-1-00179-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.50	30	0.21	0.56	56
Double Hung	NCW-K-1-00179-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	Lead Overlay	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung	NCW-K-1-00179-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	Grids <1"	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung	NCW-K-1-00179-00004	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL <1"	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung	NCW-K-1-00179-00005	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.31	1.76	0.40	24	0.21	0.44	56
Double Hung	NCW-K-1-00180-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.27	18	0.21	0.49	57
Double Hung	NCW-K-1-00180-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung	NCW-K-1-00180-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	Grids <1"	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung	NCW-K-1-00180-00004	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung	NCW-K-1-00180-00005	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.30	1.70	0.22	15	0.21	0.38	57
Double Hung	NCW-K-1-00181-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.27	22	0.21	0.48	56
Double Hung	NCW-K-1-00181-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Lead Overlay	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung	NCW-K-1-00181-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Grids <1"	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung	NCW-K-1-00181-00004	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung	NCW-K-1-00181-00005	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.27	1.53	0.21	18	0.21	0.37	56
Double Hung	NCW-K-1-00208-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.27	1.53	0.27	22	0.21	0.48	44
Double Hung	NCW-K-1-00208-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Lead Overlay	0.27	1.53	0.24	20	0.21	0.42	44
Double Hung - Roll Up Screen	NCW-K-1-00208-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.27	1.53	0.27	22	0.21	0.48	44

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Double Hung - Roll Up Screen	NCW-K-1-00208-00004	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Lead Overlay	0.27	1.53	0.24	20	0.21	0.42	44
Double Hung	NCW-K-1-00209-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Grids <1"	0.28	1.59	0.24	19	0.21	0.42	44
Double Hung - Roll Up Screen	NCW-K-1-00209-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Grids <1"	0.28	1.59	0.24	19	0.21	0.42	44
Double Hung	NCW-K-1-00210-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.29	1.65	0.21	16	0.21	0.37	44
Double Hung - Roll Up Screen	NCW-K-1-00210-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.29	1.65	0.21	16	0.21	0.37	44
Double Hung	NCW-K-1-00211-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.29	1.65	0.24	17	0.21	0.42	44
Double Hung - Roll Up Screen	NCW-K-1-00211-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.29	1.65	0.24	17	0.21	0.42	44
Double Hung	NCW-K-1-00220-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.49	28	0.21	0.56	51
Double Hung	NCW-K-1-00220-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.32	1.82	0.44	25	0.21	0.49	51
Double Hung	NCW-K-1-00220-00003	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL <1"	0.32	1.82	0.44	25	0.21	0.49	51
Double Hung - Roll Up Screen	NCW-K-1-00220-00004	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.49	28	0.21	0.56	51
Double Hung - Roll Up Screen	NCW-K-1-00220-00005	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.32	1.82	0.44	25	0.21	0.49	51
Double Hung - Roll Up Screen	NCW-K-1-00220-00006	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL <1"	0.32	1.82	0.44	25	0.21	0.49	51
Double Hung	NCW-K-1-00221-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.34	1.93	0.44	23	0.21	0.49	51
Double Hung - Roll Up Screen	NCW-K-1-00221-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.34	1.93	0.44	23	0.21	0.49	51
Double Hung	NCW-K-1-00222-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.39	2.21	0.39	14	0.21	0.43	50
Double Hung - Roll Up Screen	NCW-K-1-00222-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.39	2.21	0.39	14	0.21	0.43	50
Double Hung	NCW-K-1-00223-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.27	17	0.21	0.49	52
Double Hung	NCW-K-1-00223-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.25	15	0.21	0.43	52
Double Hung	NCW-K-1-00223-00003	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.31	1.76	0.25	15	0.21	0.43	52
Double Hung - Roll Up Screen	NCW-K-1-00223-00004	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.27	17	0.21	0.49	52
Double Hung - Roll Up Screen	NCW-K-1-00223-00005	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.25	15	0.21	0.43	52
Double Hung - Roll Up Screen	NCW-K-1-00223-00006	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL <1"	0.31	1.76	0.25	15	0.21	0.43	52
Double Hung	NCW-K-1-00224-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.33	1.87	0.25	13	0.21	0.43	52
Double Hung - Roll Up Screen	NCW-K-1-00224-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.33	1.87	0.25	13	0.21	0.43	52

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Double Hung	NCW-K-1-00225-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.38	2.16	0.22	5	0.21	0.38	51
Double Hung - Roll Up Screen	NCW-K-1-00225-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.38	2.16	0.22	5	0.21	0.38	51
Double Hung	NCW-K-1-00185-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.49	29	0.21	0.56	55
Double Hung	NCW-K-1-00185-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Lead Overlay	0.31	1.76	0.44	26	0.21	0.49	55
Double Hung	NCW-K-1-00185-00003	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Grids <1"	0.31	1.76	0.44	26	0.21	0.49	55
Double Hung	NCW-K-1-00187-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL <1"	0.31	1.76	0.44	26	0.21	0.49	55
Double Hung	NCW-K-1-00186-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.32	1.82	0.39	22	0.21	0.43	53
Double Hung	NCW-K-1-00188-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.27	18	0.21	0.49	56
Double Hung	NCW-K-1-00188-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.30	1.70	0.24	16	0.21	0.43	56
Double Hung	NCW-K-1-00188-00003	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Grids <1"	0.30	1.70	0.24	16	0.21	0.43	56
Double Hung	NCW-K-1-00190-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.31	1.76	0.24	15	0.21	0.43	56
Double Hung	NCW-K-1-00189-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.31	1.76	0.22	14	0.21	0.38	56
Double Hung	NCW-K-1-00191-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.26	22	0.21	0.47	46
Double Hung	NCW-K-1-00191-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Lead Overlay	0.26	1.48	0.24	21	0.21	0.42	46
Double Hung	NCW-K-1-00191-00003	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Grids <1"	0.26	1.48	0.24	21	0.21	0.42	46
Double Hung	NCW-K-1-00193-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.27	1.53	0.24	20	0.21	0.42	46
Double Hung	NCW-K-1-00192-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.28	1.59	0.21	17	0.21	0.37	46
Double Hung	NCW-K-1-00226-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.27	20	0.21	0.47	42
Double Hung	NCW-K-1-00226-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Lead Overlay	0.28	1.59	0.24	19	0.21	0.42	42
Double Hung	NCW-K-1-00226-00003	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.28	1.59	0.24	19	0.21	0.42	42
Double Hung - Roll Up Screen	NCW-K-1-00226-00004	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.27	20	0.21	0.47	42
Double Hung - Roll Up Screen	NCW-K-1-00226-00005	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Lead Overlay	0.28	1.59	0.24	19	0.21	0.42	42
Double Hung - Roll Up Screen	NCW-K-1-00226-00006	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL <1"	0.28	1.59	0.24	19	0.21	0.42	42
Double Hung	NCW-K-1-00227-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Grids <1"	0.29	1.65	0.24	17	0.21	0.42	42
Double Hung - Roll Up Screen	NCW-K-1-00227-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	Grids <1"	0.29	1.65	0.24	17	0.21	0.42	42

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Double Hung	NCW-K-1-00228-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.32	1.82	0.21	12	0.21	0.37	37
Double Hung - Roll Up Screen	NCW-K-1-00228-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.32	1.82	0.21	12	0.21	0.37	37
Double Hung	NCW-K-1-00235-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.24	21	0.21	0.46	45
Double Hung	NCW-K-1-00236-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL >=1"	0.28	1.59	0.19	16	0.21	0.36	45
Double Hung	NCW-K-1-00237-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.27	1.53	0.22	19	0.21	0.41	45
Double Hung	NCW-K-1-00238-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Resto	-	0.30	1.70	0.24	16	0.21	0.46	40
Double Hung - Roll Up Screen	NCW-K-1-00179-00006	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.50	30	0.21	0.56	56
Double Hung - Roll Up Screen	NCW-K-1-00179-00007	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	Lead Overlay	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung - Roll Up Screen	NCW-K-1-00179-00008	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	Grids <1"	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung - Roll Up Screen	NCW-K-1-00179-00009	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL <1"	0.31	1.76	0.45	27	0.21	0.50	56
Double Hung - Roll Up Screen	NCW-K-1-00179-00010	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.31	1.76	0.40	24	0.21	0.44	56
Double Hung - Roll Up Screen	NCW-K-1-00180-00006	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.27	18	0.21	0.49	57
Double Hung - Roll Up Screen	NCW-K-1-00180-00007	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung - Roll Up Screen	NCW-K-1-00180-00008	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	Grids <1"	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung - Roll Up Screen	NCW-K-1-00180-00009	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.30	1.70	0.24	16	0.21	0.44	57
Double Hung - Roll Up Screen	NCW-K-1-00180-00010	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.30	1.70	0.22	15	0.21	0.38	57
Double Hung - Roll Up Screen	NCW-K-1-00181-00006	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.27	22	0.21	0.48	56
Double Hung - Roll Up Screen	NCW-K-1-00181-00007	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Lead Overlay	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung - Roll Up Screen	NCW-K-1-00181-00008	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Grids <1"	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung - Roll Up Screen	NCW-K-1-00181-00009	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.27	1.53	0.24	20	0.21	0.42	56
Double Hung - Roll Up Screen	NCW-K-1-00181-00010	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.27	1.53	0.21	18	0.21	0.37	56
Double Hung - Roll Up Screen	NCW-K-1-00185-00004	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.49	29	0.21	0.56	55
Double Hung - Roll Up Screen	NCW-K-1-00185-00005	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Lead Overlay	0.31	1.76	0.44	26	0.21	0.49	55
Double Hung - Roll Up Screen	NCW-K-1-00185-00006	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Grids <1"	0.31	1.76	0.44	26	0.21	0.49	55
Double Hung - Roll Up Screen	NCW-K-1-00187-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL <1"	0.32	1.82	0.44	25	0.21	0.49	55

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Double Hung - Roll Up Screen	NCW-K-1-00186-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.32	1.82	0.39	22	0.21	0.43	55
Double Hung - Roll Up Screen	NCW-K-1-00188-00004	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.27	18	0.21	0.49	56
Double Hung - Roll Up Screen	NCW-K-1-00188-00005	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.30	1.70	0.24	16	0.21	0.43	56
Double Hung - Roll Up Screen	NCW-K-1-00188-00006	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Grids <1"	0.30	1.70	0.24	16	0.21	0.43	56
Double Hung - Roll Up Screen	NCW-K-1-00190-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL <1"	0.31	1.76	0.24	15	0.21	0.43	56
Double Hung - Roll Up Screen	NCW-K-1-00189-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.31	1.76	0.22	14	0.21	0.38	56
Double Hung - Roll Up Screen	NCW-K-1-00191-00004	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.26	22	0.21	0.47	46
Double Hung - Roll Up Screen	NCW-K-1-00191-00005	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Lead Overlay	0.26	1.48	0.24	21	0.21	0.42	46
Double Hung - Roll Up Screen	NCW-K-1-00191-00006	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	Grids <1"	0.26	1.48	0.24	21	0.21	0.42	46
Double Hung - Roll Up Screen	NCW-K-1-00193-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL <1"	0.27	1.53	0.24	20	0.21	0.42	46
Double Hung - Roll Up Screen	NCW-K-1-00192-00002	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.28	1.59	0.21	17	0.21	0.37	46
French Door - 3/4 Lite	NCW-K-6-00486-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.34	1.93	0.13	5	0.14	0.22	60
French Door - 3/4 Lite	NCW-K-6-00486-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Interior Grille Only	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00486-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00487-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	1-1/4" SDL w/ Grille	0.35	1.99	0.11	3	0.14	0.19	60
French Door - 3/4 Lite	NCW-K-6-00488-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	5/8" SDL w/ Grille	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00489-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	3/4"-1" SDL w/ Grille	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00482-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.34	1.93	0.13	5	0.14	0.22	60
French Door - 3/4 Lite	NCW-K-6-00482-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Interior Grille Only	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00482-00003	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00482-00004	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	1-1/4" SDL w/ Grille	0.34	1.93	0.11	4	0.14	0.19	60
French Door - 3/4 Lite	NCW-K-6-00482-00005	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	3/4"-1" SDL w/ Grille	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00483-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	5/8" SDL w/ Grille	0.34	1.93	0.12	4	0.14	0.20	60
French Door - 3/4 Lite	NCW-K-6-00490-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.34	1.93	0.13	5	0.14	0.22	58
French Door - 3/4 Lite	NCW-K-6-00490-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.34	1.93	0.12	4	0.14	0.20	58

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
French Door - 3/4 Lite	NCW-K-6-00491-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	1-1/4" SDL w/ Grille	0.36	2.04	0.11	1	0.14	0.19	58
French Door - 3/4 Lite	NCW-K-6-00492-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	5/8" SDL w/ Grille	0.36	2.04	0.12	2	0.14	0.20	58
French Door - 3/4 Lite	NCW-K-6-00493-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	3/4"-1" SDL w/ Grille	0.35	1.99	0.12	3	0.14	0.20	58
French Door - 3/4 Lite	NCW-K-6-00494-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Interior Grille Only	0.35	1.99	0.12	3	0.14	0.20	58
French Door - Full Lite	NCW-K-6-00545-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.42	24	0.14	0.47	59
French Door - Full Lite	NCW-K-6-00545-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.32	1.82	0.37	21	0.14	0.40	59
French Door - Full Lite	NCW-K-6-00545-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.32	1.82	0.37	21	0.14	0.40	59
French Door - Full Lite	NCW-K-6-00546-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.33	1.87	0.31	17	0.14	0.34	59
French Door - Full Lite	NCW-K-6-00547-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.37	20	0.14	0.40	59
French Door - Full Lite	NCW-K-6-00548-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.23	14	0.14	0.41	60
French Door - Full Lite	NCW-K-6-00548-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.20	13	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00548-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.31	1.76	0.20	13	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00549-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.32	1.82	0.17	10	0.14	0.30	60
French Door - Full Lite	NCW-K-6-00550-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.20	11	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00537-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.32	1.82	0.42	24	0.14	0.46	60
French Door - Full Lite	NCW-K-6-00537-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Lead Overlay	0.32	1.82	0.36	21	0.14	0.41	60
French Door - Full Lite	NCW-K-6-00537-00003	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	Grids <1"	0.32	1.82	0.36	21	0.14	0.41	60
French Door - Full Lite	NCW-K-6-00537-00004	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.32	1.82	0.31	18	0.14	0.33	60
French Door - Full Lite	NCW-K-6-00538-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.33	1.87	0.36	19	0.14	0.40	60
French Door - Full Lite	NCW-K-6-00557-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.41	24	0.14	0.48	58
French Door - Full Lite	NCW-K-6-00557-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Lead Overlay	0.32	1.82	0.36	21	0.14	0.40	58
French Door - Full Lite	NCW-K-6-00557-00003	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	Grids <1"	0.32	1.82	0.36	21	0.14	0.40	58
French Door - Full Lite	NCW-K-6-00558-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.34	1.93	0.31	15	0.14	0.33	58
French Door - Full Lite	NCW-K-6-00559-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.36	19	0.14	0.40	58
French Door - Full Lite	NCW-K-6-00539-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.23	14	0.14	0.41	60

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
French Door - Full Lite	NCW-K-6-00539-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Lead Overlay	0.31	1.76	0.20	13	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00539-00003	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	Grids <1"	0.31	1.76	0.20	13	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00539-00004	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL 1 1/4"	0.31	1.76	0.17	11	0.14	0.29	60
French Door - Full Lite	NCW-K-6-00540-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.32	1.82	0.20	11	0.14	0.35	60
French Door - Full Lite	NCW-K-6-00560-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.23	14	0.14	0.41	59
French Door - Full Lite	NCW-K-6-00560-00002	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Lead Overlay	0.31	1.76	0.20	13	0.14	0.35	59
French Door - Full Lite	NCW-K-6-00560-00003	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	Grids <1"	0.31	1.76	0.20	13	0.14	0.35	59
French Door - Full Lite	NCW-K-6-00561-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL 1 1/4"	0.33	1.87	0.17	9	0.14	0.29	59
French Door - Full Lite	NCW-K-6-00562-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.20	11	0.14	0.35	59
French Door - Full Lite	NCW-K-6-00601-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.28	1.59	0.20	16	0.14	0.38	49
French Door - Full Lite	NCW-K-6-00601-00002	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL >=1"	0.28	1.59	0.15	14	0.14	0.28	49
French Door - Full Lite	NCW-K-6-00602-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.29	1.65	0.18	14	0.14	0.33	49
French Door - Full Lite	NCW-K-6-00603-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.28	1.59	0.21	17	0.14	0.39	48
French Door - Full Lite	NCW-K-6-00603-00002	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL >=1"	0.28	1.59	0.16	14	0.14	0.28	48
French Door - Full Lite	NCW-K-6-00604-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.29	1.65	0.18	14	0.14	0.33	48
French Door - Full Lite	NCW-K-6-00605-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.21	17	0.14	0.38	46
French Door - Full Lite	NCW-K-6-00606-00002	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL >=1"	0.31	1.76	0.16	10	0.14	0.28	45
French Door - Full Lite	NCW-K-6-00607-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.31	1.76	0.18	12	0.14	0.33	45
French Door - Full Lite	NCW-K-6-00608-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.21	16	0.14	0.39	46
French Door - Full Lite	NCW-K-6-00609-00002	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL >=1"	0.31	1.76	0.16	10	0.14	0.28	45
French Door - Full Lite	NCW-K-6-00610-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.31	1.76	0.19	12	0.14	0.33	45
Picture	NCW-K-27-00023-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	-	-	0.27	1.53	0.34	26	0.06	0.63	60
Picture	NCW-K-27-00027-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	-	0.23	1.31	0.34	31	0.06	0.61	49
Picture	NCW-K-27-00024-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	-	-	0.27	1.53	0.34	26	0.06	0.63	59
Picture	NCW-K-27-00028-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	-	0.22	1.25	0.33	32	0.06	0.61	48

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Picture	NCW-K-27-00023-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	-	SDL<1"	0.27	1.53	0.31	24	0.06	0.57	60
Picture	NCW-K-27-00023-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	-	SDL>=1"	0.27	1.53	0.28	22	0.06	0.51	60
Picture	NCW-K-27-00027-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL<1"	0.23	1.31	0.31	29	0.06	0.55	49
Picture	NCW-K-27-00027-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL>=1"	0.23	1.31	0.28	27	0.06	0.49	49
Picture	NCW-K-27-00025-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	-	SDL>=1"	0.29	1.65	0.28	20	0.06	0.50	59
Picture	NCW-K-27-00026-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	-	SDL<1"	0.28	1.59	0.31	23	0.06	0.56	59
Picture	NCW-K-27-00029-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL>=1"	0.24	1.36	0.27	26	0.06	0.49	48
Picture	NCW-K-27-00030-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL<1"	0.24	1.36	0.30	27	0.06	0.55	48
Picture	NCW-K-27-00039-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	-	-	0.28	0.30	0.64	70	0.06	0.72	59
Picture	NCW-K-27-00039-00002	Double, 4mm	8071 #3	Thermoplastic	Argon	-	SDL<1"	0.28	0.30	0.58	67	0.06	0.65	59
Picture	NCW-K-27-00039-00003	Double, 4mm	8071 #3	Thermoplastic	Argon	-	SDL>=1"	0.28	0.30	0.52	63	0.06	0.58	59
Picture	NCW-K-27-00040-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	-	-	0.28	0.30	0.63	70	0.06	0.72	58
Picture	NCW-K-27-00041-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	-	SDL>=1"	0.30	0.30	0.51	63	0.06	0.58	58
Picture	NCW-K-27-00042-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	-	SDL<1"	0.30	0.30	0.57	66	0.06	0.64	58
Picture	NCW-K-27-00043-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	-	0.22	0.30	0.30	51	0.06	0.59	48
Picture	NCW-K-27-00044-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL>=1"	0.24	0.30	0.25	48	0.06	0.47	48
Picture	NCW-K-27-00045-00001	Double, 4mm + 6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	-	SDL<1"	0.23	0.30	0.28	49	0.06	0.53	48
Transom - 1.56 Stile	NCW-K-5-00181-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.29	20	0.21	0.52	55
Transom - 1.56 Stile	NCW-K-5-00181-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.29	1.65	0.26	19	0.21	0.47	55
Transom - 1.56 Stile	NCW-K-5-00181-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.29	1.65	0.24	17	0.21	0.42	55
Transom - 1.56 Stile	NCW-K-5-00203-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.29	20	0.21	0.52	55
Transom - 1.56 Stile	NCW-K-5-00204-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.24	12	0.21	0.42	55
Transom - 1.56 Stile	NCW-K-5-00205-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.27	15	0.21	0.47	55
Transom - 1.56 Stile	NCW-K-5-00185-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.26	1.48	0.28	23	0.21	0.51	47
Transom - 1.56 Stile	NCW-K-5-00185-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.26	22	0.21	0.46	47

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Transom - 1.56 Stile	NCW-K-5-00185-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.26	1.48	0.23	21	0.21	0.41	47
Transom - 1.56 Stile	NCW-K-5-00182-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.29	1.65	0.29	20	0.21	0.52	57
Transom - 1.56 Stile	NCW-K-5-00183-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.24	16	0.21	0.42	57
Transom - 1.56 Stile	NCW-K-5-00184-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.29	1.65	0.26	19	0.21	0.47	57
Transom - 1.56 Stile	NCW-K-5-00206-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.29	20	0.21	0.52	54
Transom - 1.56 Stile	NCW-K-5-00207-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.24	12	0.21	0.42	54
Transom - 1.56 Stile	NCW-K-5-00208-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.26	15	0.21	0.47	54
Transom - 1.56 Stile	NCW-K-5-00186-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.25	1.42	0.28	25	0.21	0.50	46
Transom - 1.56 Stile	NCW-K-5-00187-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.26	1.48	0.23	21	0.21	0.40	46
Transom - 1.56 Stile	NCW-K-5-00188-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.26	22	0.21	0.45	46
Transom - 1.56 Stile	NCW-K-5-00209-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.28	23	0.21	0.51	44
Transom - 1.56 Stile	NCW-K-5-00210-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.28	1.59	0.23	18	0.21	0.41	44
Transom - 1.56 Stile	NCW-K-5-00211-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.28	1.59	0.26	20	0.21	0.46	44
Transom - 1.56 Stile	NCW-K-5-00212-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.26	1.48	0.28	23	0.21	0.50	44
Transom - 1.56 Stile	NCW-K-5-00213-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.28	1.59	0.23	18	0.21	0.40	43
Transom - 1.56 Stile	NCW-K-5-00214-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.28	1.59	0.26	20	0.21	0.45	43
Transom - 1.56 Stile	NCW-K-5-00327-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.53	33	0.21	0.59	58
Transom - 1.56 Stile	NCW-K-5-00327-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.48	30	0.21	0.54	58
Transom - 1.56 Stile	NCW-K-5-00327-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.44	28	0.21	0.48	58
Transom - 1.56 Stile	NCW-K-5-00328-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.52	32	0.21	0.59	56
Transom - 1.56 Stile	NCW-K-5-00329-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.43	26	0.21	0.48	56
Transom - 1.56 Stile	NCW-K-5-00330-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.47	28	0.21	0.53	56
Transom - 1.56 Stile	NCW-K-5-00331-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.53	32	0.21	0.59	55
Transom - 1.56 Stile	NCW-K-5-00332-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.43	22	0.21	0.48	54
Transom - 1.56 Stile	NCW-K-5-00333-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.48	26	0.21	0.54	54

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Transom - 1.56 Stile	NCW-K-5-00334-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.52	31	0.21	0.59	54
Transom - 1.56 Stile	NCW-K-5-00335-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.43	22	0.21	0.48	54
Transom - 1.56 Stile	NCW-K-5-00336-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.47	26	0.21	0.53	54
Transom - 1.56 Stile	NCW-K-5-00357-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.25	1.42	0.26	24	0.21	0.49	45
Transom - 1.56 Stile	NCW-K-5-00358-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.26	1.48	0.21	19	0.21	0.39	45
Transom - 1.56 Stile	NCW-K-5-00359-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.26	1.48	0.23	21	0.21	0.44	45
Transom - 1.56 Stile	NCW-K-5-00366-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.29	1.65	0.26	19	0.21	0.49	40
Transom - 2.53 Stile	NCW-K-5-00231-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.26	17	0.21	0.45	56
Transom - 2.53 Stile	NCW-K-5-00231-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.23	16	0.21	0.41	56
Transom - 2.53 Stile	NCW-K-5-00231-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.21	14	0.21	0.36	56
Transom - 2.53 Stile	NCW-K-5-00253-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.26	17	0.21	0.45	56
Transom - 2.53 Stile	NCW-K-5-00254-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.21	11	0.21	0.36	56
Transom - 2.53 Stile	NCW-K-5-00255-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.23	13	0.21	0.41	56
Transom - 2.53 Stile	NCW-K-5-00235-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.25	20	0.21	0.44	48
Transom - 2.53 Stile	NCW-K-5-00235-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.27	1.53	0.23	19	0.21	0.39	48
Transom - 2.53 Stile	NCW-K-5-00235-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.27	1.53	0.21	18	0.21	0.35	48
Transom - 2.53 Stile	NCW-K-5-00232-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.25	17	0.21	0.45	58
Transom - 2.53 Stile	NCW-K-5-00233-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.21	13	0.21	0.36	58
Transom - 2.53 Stile	NCW-K-5-00234-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.23	16	0.21	0.40	58
Transom - 2.53 Stile	NCW-K-5-00256-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.26	17	0.21	0.45	55
Transom - 2.53 Stile	NCW-K-5-00257-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.21	11	0.21	0.36	55
Transom - 2.53 Stile	NCW-K-5-00258-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.32	1.82	0.23	13	0.21	0.40	55
Transom - 2.53 Stile	NCW-K-5-00236-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.25	20	0.21	0.44	47
Transom - 2.53 Stile	NCW-K-5-00237-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.28	1.59	0.20	16	0.21	0.35	47
Transom - 2.53 Stile	NCW-K-5-00238-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.27	1.53	0.23	19	0.21	0.39	47

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Transom - 2.53 Stile	NCW-K-5-00259-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.25	19	0.21	0.44	45
Transom - 2.53 Stile	NCW-K-5-00260-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.30	1.70	0.21	14	0.21	0.35	44
Transom - 2.53 Stile	NCW-K-5-00261-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.23	17	0.21	0.39	45
Transom - 2.53 Stile	NCW-K-5-00262-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.25	19	0.21	0.44	44
Transom - 2.53 Stile	NCW-K-5-00263-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.29	1.65	0.20	15	0.21	0.35	44
Transom - 2.53 Stile	NCW-K-5-00264-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.23	17	0.21	0.39	44
Transom - 2.53 Stile	NCW-K-5-00337-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.47	28	0.21	0.52	59
Transom - 2.53 Stile	NCW-K-5-00337-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.42	25	0.21	0.46	59
Transom - 2.53 Stile	NCW-K-5-00337-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.38	23	0.21	0.41	59
Transom - 2.53 Stile	NCW-K-5-00338-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.46	28	0.21	0.52	57
Transom - 2.53 Stile	NCW-K-5-00339-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.32	1.82	0.37	21	0.21	0.41	57
Transom - 2.53 Stile	NCW-K-5-00340-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.42	25	0.21	0.46	57
Transom - 2.53 Stile	NCW-K-5-00341-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.47	28	0.21	0.52	55
Transom - 2.53 Stile	NCW-K-5-00342-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.38	19	0.21	0.41	55
Transom - 2.53 Stile	NCW-K-5-00343-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.42	23	0.21	0.46	55
Transom - 2.53 Stile	NCW-K-5-00344-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.46	28	0.21	0.52	55
Transom - 2.53 Stile	NCW-K-5-00345-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.37	19	0.21	0.41	55
Transom - 2.53 Stile	NCW-K-5-00346-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.41	22	0.21	0.46	55
Transom - 2.53 Stile	NCW-K-5-00360-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.23	19	0.21	0.43	45
Transom - 2.53 Stile	NCW-K-5-00361-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.28	1.59	0.19	16	0.21	0.34	45
Transom - 2.53 Stile	NCW-K-5-00362-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.27	1.53	0.21	18	0.21	0.38	45
Transom - 2.53 Stile	NCW-K-5-00367-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.23	16	0.21	0.43	41
Transom - 2.75 Stile	NCW-K-5-00281-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.25	17	0.21	0.44	56
Transom - 2.75 Stile	NCW-K-5-00281-00002	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.30	1.70	0.23	16	0.21	0.39	56
Transom - 2.75 Stile	NCW-K-5-00281-00003	Double, 3mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.30	1.70	0.20	14	0.21	0.35	56

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Transom - 2.75 Stile	NCW-K-5-00303-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	-	0.30	1.70	0.25	17	0.21	0.44	56
Transom - 2.75 Stile	NCW-K-5-00304-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.21	9	0.21	0.35	56
Transom - 2.75 Stile	NCW-K-5-00305-00001	Double, 3mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.23	12	0.21	0.39	56
Transom - 2.75 Stile	NCW-K-5-00285-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.24	20	0.21	0.43	48
Transom - 2.75 Stile	NCW-K-5-00285-00002	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.27	1.53	0.22	19	0.21	0.38	48
Transom - 2.75 Stile	NCW-K-5-00285-00003	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.27	1.53	0.20	18	0.21	0.34	48
Transom - 2.75 Stile	NCW-K-5-00282-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	-	0.30	1.70	0.25	17	0.21	0.44	58
Transom - 2.75 Stile	NCW-K-5-00283-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.20	13	0.21	0.35	58
Transom - 2.75 Stile	NCW-K-5-00284-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.22	14	0.21	0.39	58
Transom - 2.75 Stile	NCW-K-5-00307-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL>=1"	0.33	1.87	0.20	10	0.21	0.35	55
Transom - 2.75 Stile	NCW-K-5-00308-00001	Double, 4mm	CG70#2	Thermoplastic	Argon	Restoration	SDL<1"	0.33	1.87	0.23	12	0.21	0.39	55
Transom - 2.75 Stile	NCW-K-5-00286-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.24	20	0.21	0.42	47
Transom - 2.75 Stile	NCW-K-5-00287-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.28	1.59	0.20	16	0.21	0.34	47
Transom - 2.75 Stile	NCW-K-5-00288-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.28	1.59	0.22	17	0.21	0.38	47
Transom - 2.75 Stile	NCW-K-5-00309-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.24	19	0.21	0.43	45
Transom - 2.75 Stile	NCW-K-5-00310-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.30	1.70	0.20	14	0.21	0.34	44
Transom - 2.75 Stile	NCW-K-5-00311-00001	Double, 3mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.22	16	0.21	0.38	45
Transom - 2.75 Stile	NCW-K-5-00312-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.28	1.59	0.24	19	0.21	0.42	44
Transom - 2.75 Stile	NCW-K-5-00313-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL>=1"	0.30	1.70	0.20	14	0.21	0.34	44
Transom - 2.75 Stile	NCW-K-5-00314-00001	Double, 4mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	SDL<1"	0.29	1.65	0.22	16	0.21	0.38	44
Transom - 2.75 Stile	NCW-K-5-00347-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.45	27	0.21	0.50	59
Transom - 2.75 Stile	NCW-K-5-00347-00002	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.31	1.76	0.41	25	0.21	0.45	59
Transom - 2.75 Stile	NCW-K-5-00347-00003	Double, 3mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.31	1.76	0.37	22	0.21	0.40	59
Transom - 2.75 Stile	NCW-K-5-00348-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	-	0.31	1.76	0.45	27	0.21	0.50	58
Transom - 2.75 Stile	NCW-K-5-00349-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL>=1"	0.32	1.82	0.36	21	0.21	0.40	57

PRODUCT	NFRC CPD	PANES	GLASS TYPE	SPACER	GAS FILL	STYLE	GRILL OPTION	U-FACTOR	U-FACTOR Metric	SHGC	ER - Canada	Air Int/Exf (L/s-m²)	VT	CR
Transom - 2.75 Stile	NCW-K-5-00350-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Ovalo	SDL<1"	0.32	1.82	0.40	23	0.21	0.45	57
Transom - 2.75 Stile	NCW-K-5-00351-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.45	26	0.21	0.50	56
Transom - 2.75 Stile	NCW-K-5-00352-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.37	19	0.21	0.40	55
Transom - 2.75 Stile	NCW-K-5-00353-00001	Double, 3mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.34	1.93	0.41	21	0.21	0.45	56
Transom - 2.75 Stile	NCW-K-5-00354-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	-	0.32	1.82	0.45	26	0.21	0.50	55
Transom - 2.75 Stile	NCW-K-5-00355-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL>=1"	0.34	1.93	0.36	18	0.21	0.40	55
Transom - 2.75 Stile	NCW-K-5-00356-00001	Double, 4mm	8071 #3	Thermoplastic	Argon	Restoration	SDL<1"	0.34	1.93	0.40	20	0.21	0.45	55
Transom - 2.75 Stile	NCW-K-5-00363-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	-	0.27	1.53	0.22	19	0.21	0.41	45
Transom - 2.75 Stile	NCW-K-5-00364-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL>=1"	0.28	1.59	0.18	15	0.21	0.33	45
Transom - 2.75 Stile	NCW-K-5-00365-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Ovalo	SDL<1"	0.28	1.59	0.20	16	0.21	0.37	45
Transom - 2.75 Stile	NCW-K-5-00368-00001	Double, 4mm+6mm	CG70#2 + IS20 #4	Thermoplastic	Argon	Restoration	-	0.31	1.76	0.22	14	0.21	0.41	41